

Technical Data Sheet

primere

by metadynea

Primere 72 J230

Phenol-formaldehyde resin

TC (technical conditions) 2221-012-72149825-2014

Description

Primere 72 J230 is a liquid condensation product of phenol and formaldehyde used as bonding in insulation wool manufactory.

Specification

Parameter	Range of values	Method
Appearance	Reddish brown liquid	Internal TC, p.4.2
pH at 20°C	8,9 ÷ 9,7	Internal TC, p.4.4
Density at 20°C, kg/l	1,190 ÷ 1,215	GOST 18329-73 method 2
Solid content (0,6g /2h/130°C), %	53 ÷ 55	Internal TC, p.4.3
Water dilutability at 20°C, g/g	≥ 20	Internal TC, p.4.5
Storage stability at 20°C, days	14	-
Free formaldehyde content, %	≤ 0,6	ISO 9397-97, titration
Free phenol content, %	≤ 0,7	ISO 8974-02

Form of delivery

Product is delivered in tank trucks.

Storage conditions

Primere 72 J230 can be stored in stainless steel tanks. Zinc or aluminium tanks are not suitable for storage of phenolic resins.

Recommended storage temperature is 18 - 20°C. Temperature should not be under 17°C

Shelf life at 20°C is about 2 weeks.

General recommendations and additional information

The gelation time of Primere 72 J230 is about 1,5-3 min.

Safety precautions

Phenol formaldehyde resins may sensitize some people. The resins contains small amount of free formaldehyde to which some people are oversensitive. The product also contains free phenol. Allergic persons should avoid places where the product is used. The concentration of formaldehyde in the air should be maintained under maximum allowed value by adequate ventilation. When handling the resin, wear protective clothing including gloves, masks or goggles. In case of contact with skin, eyes or clothing, flush area with plenty of water. Additional information is given in the Material Safety Data Sheet.

For further technical information, please contact Technical Service.

NOTE! The information in this leaflet is, to the best of our knowledge, true and accurate. Any recommendations or suggestions are made without warranty or guarantee, since the conditions of use are beyond our control. We further point out that patents may exist for certain applications.