

Technical Data Sheet

Primere 88N8133

Powder resin

Description

Primere 88N8133 is the binding agent for refractory industry – solid powder mixture of novolac resin and HMTA.

Specification

| Parameter | Range of values | Method |
|--|----------------------------------|---------------------|
| Appearance | Powder from white to brown color | - |
| Flow distance, mm | 45 ÷ 55 | DIN-EN-ISO-8619-98 |
| HMTA content, % | 13,5 | DIN 16916, ISO 8988 |
| Water content, (Karl Fisher), % | ≤ 1 | ISO 760 |
| Grinding fineness, residue sieve 0,09mm, % | ≤ 2 | ISO 4610 |
| Free phenol content, % | ≤ 1 | DIN EN ISO 8974 |

Form of delivery

Supplied in big bags of 500 kg or bags 25-30 kg.

Storage conditions

The binder is stored in a dry ventilated place, preventing from direct sunlight and precipitation, at a temperature not exceeding 25 ° C. Shelf life - 6 months

Safety precautions

The binder has an irritating effect on the skin, mucous membranes of the eyes, respiratory system. When working should wear gloves, goggles, overalls and safety shoes. Additional information is given in the Material Safety Data Sheet. For further technical information, please contact Technical Service.

NOTE! The information in this leaflet is, to the best of our knowledge, true and accurate. Any recommendations or suggestions are made without warranty or guarantee, since the conditions of use are beyond our control. We further point out that patents may exist for certain applications.